


Very hazy, non PCV-based laminated MDF, with a treated surface, allowing it to increase resistance to scratch and chemical products

Laminated back surface (same color). Plated edges on the 4 sides



| | |
|------------------|------------------------|
| Height | 100mm to 2700mm |
| Width | 100mm to 1200mm |
| Thickness | 18mm |

INFORMATION ON THE MATÉRIALS:

Support

- High-density fireboard panel
- Formaldehyde Emission : ClassE1
- Melamine back surface
- Thickness tolerance: +/-0.3mm
- Density: 800 Kg/ m3

Face

- Polymer-treated thickness: 0.3mm

Glue

- Polyurethane glue (PURE)
- High adhesion
- High resistance to heat and humidity

Edges

- ♠ PVC and ABS
- ♠ Thickness: 0.5mm and 1.5mm

FIELD OF USE

- Kitchen façades
- façades (or sides) for bathroom furniture
- Walk-in wardrobes' doors (dressings' doors)
- Arrangement

CHARACTÉRISTICS

- Abrasion resistance: Class (2D)
- Scratch Resistance: Class (2A)
- Temperature Resistance: Class 5 (>75°)
- Climatic variation resistance: Classe 3
- Brightness: < 5 (Super Mat)
- Light stability: >= 6 (Blue scale)

CHEMICAL RESISTANCE

| Substance Chimique | Temps d'exposition | Résultat |
|-------------------------|--------------------|-------------------|
| Acetic Acid | 16h | No visible change |
| Citric acid | 16h | No visible change |
| Ammonia | 16h | No visible change |
| Ethyl Alcohol | 16h | No visible change |
| Red Wine | 16h | No visible change |
| Beer | 16h | No visible change |
| Cola | 16h | No visible change |
| Black tea | 16h | No visible change |
| Eau | 16h | No visible change |
| Gazoline | 16h | No visible change |
| Acetone | 16h | No visible change |
| Ethylene butyl acrylate | 16h | No visible change |
| Butter | 16h | No visible change |
| Olive oil | 16h | No visible change |
| Mustard | 16h | No visible change |
| Onion | 16h | No visible change |
| Désinfectant | 16h | No visible change |
| ink | 16h | No visible change |
| Cleaning product | 16h | No visible change |
| Solvent | 16h | No visible change |

